

EPOXIES

F-01

TECHNICAL DATA SHEET

COMPONENTS

2

SOLIDS

100%

VOC

<50 g/l

MIX RATIO

2:1

DESCRIPTION

F-01 is our workhorse, clear, 100% solids epoxy. It can be ordered with 2 different speeds of hardeners- Standard and Fast. This allows for easy transition between cold and warm weather applications and cure times. It can be used with our full line of colorants (PN 1339) to provide extreme color flexibility. Ease of use, good flow and leveling, toughness and flexibility are characteristics of this high quality epoxy. The cured material has good, broad-range, chemical resistance as well as good abrasion and impact resistance.

RECOMMENDED USES

F-01 is most often used as a primer, broadcast resin and topcoat for resinous concrete flooring projects. It can also be used as a patching or trowel material when combined with PN 1170 or PN 1324 aggregate.

LIMITATIONS

F-01 is designed to be applied at 8-12 mils as a primer, 12-20 mils as a body coat and 10-16 mils as a topcoat. Ideal application temperatures to be between 60 – 85°F. Cooler temperatures will increase cure times. Warmer temperatures will decrease working and cure times. Polymer Nation has tested its materials with our PN 1338 metallic powders. While we have taken every precaution to formulate an exceptional epoxy coating, certain undesired results in so-called epoxy metallic systems in which Polymer Nation resins are used (i.e. F-01, F-41, P-01) may occur due to a number of factors including mixing, placement techniques and thermal variations in the installation area. Good coating practices are required when installing our coatings. See our Solution Guide for helpful information. Verify that substrate temperature is above 5 degrees of dewpoint during application and cure of material to avoid a potential amine blush.

SURFACE PREPARATION

The preparation method for each project is determined by a full understanding of the substrate to be coated, the chemistry of the coating system being used, the coating system thickness, and numerous other factors. The coating installer should fully read and understand ICRI Guideline NO. 310.2R-2013 and OSHA 29 CFR 1926.1153 before starting preparatory work. The aim, of preparing a substrate for coating applications, is to roughen the surface, remove weak layers, contaminants, dirt, debris and present a solid, clean, dry substrate for the primer. If unsure as to the level of preparation needed contact Polymer Nation at Lab@polymerNation.com.

MIXING

It is always recommended to mix the entire kit, whenever possible, to avoid off-ratio mixtures. Mix ratio is 2 parts F-01 Resin (Part A) to 1 part F-01 Hardener (Part B). Combine all of part A and B into a single container, large enough to except the entire kit. Mix using a 350 RPM mixer using an appropriate mixing blade for 1.5 – 2.5 minutes making sure to not introduce excessive air into the material.

APPLICATION

Pour entire content of mixed material onto the floor in ribbons. Spread material using a flat blade or notched squeegee. Back roll material using a 3/8" nap roller cover to maintain an even mil thickness of material. To make an epoxy patching material mix no more material than can be mixed and applied within the stated gel time and add the selected aggregate until the desired thickness is achieved. Recoat within 24 hours. Clean tools with a solvent similar to Xylene or Acetone.

COMPONENTS



Part A



Part B

GENERAL PRODUCT INFORMATION

Chemistry	Epoxies
Color / Finish	Clear and Color Packs
Number of Components	2
Solids by Volume	100%
VOC (Mixed)	<50 g/l
Mix Ratio	2:1
Mixed Viscosity	500-600 cP 25°C/77°F
Gel / Working Time	25-35/10-15 minutes
Application Temperature	60 – 85°F
Odor	Subtle

It is always recommended to mix the entire kit, whenever possible, to avoid off-ratio mixtures

Warmer temperatures will reduce viscosity and lower temperatures will increase viscosity

Standard/Fast

PHYSICAL PROPERTIES

Hardness	D65 @ 24 hours / D78 @ 7 days (Standard); D65 @ 4 hours / D75 @ 24 hours (Fast)	
Tensile Strength	2,870 psi	ASTM C307
Compressive Strength	13,000 psi	ASTM C579
Flexural Strength	5,750 psi	ASTM C580
Abrasion – Taber CS-17	0.053g Loss (when higher abrasion resistance is required the addition of PC 1336 to the coating should be included)	ASTM D4060
Impact Resistance	>160 inch pounds	ASTM D2794
Adhesion to Concrete	>450 Substrate failure	ASTM D7234
Gloss @ 60°	90+	
Color Scale	0.5-1.0	ASTM D1500
Accelerated Weathering	Moderate yellowing	ASTM G154
Moisture Absorption	<.2 weight increase	ASTM C413
Coefficient of Thermal Lineal Expansion	15-17 x 10 ⁻⁶ 27-30 x 10 ⁻⁶	ASTM C531
Water Vapor Transmission	See ASTM D3010	ASTM D1653
Independent Certificate – Third-Party Testing	N/A	ASTM D3010
Adhesion	5A	ASTM D3359
Adhesion to Steel	>1,000 psi	ASTM D4541
Hiding Power	2-5/200	ASTM D5150
Flammability When Adhered to Concrete	Self-Extinguishing	ASTM D635
Coefficient of Friction – Dry	0.75	NFSI B101.0
Coefficient of Friction – Wet	0.7	NFSI B101.1

Shore D Hardness (Standard) / Shore D Hardness (Fast)

ASTM D4060 – Abrasion Resistance CS17 1000 g 1000cycles in g Loss

Applying material close to dew point will decrease gloss and may result in an amine blush

CURE SCHEDULE

Dry to Touch	6-8/3-4 hours
Through Dry	8-10/4-5 hours
Dry to Light Use	16-24/4-8 hours
Full Cure	7 days

COVERAGE & PACKAGING

Coverage Rate	80 – 200 sq. ft./gal.
Application Thickness	8-20 mils
Recoat Window	Recoat within 24 hours
Packaging	3, 15 & 165 Gallon Kits

STORAGE, HANDLING & SAFETY

Store at 60-80 degrees F. Store material between 60-80 degrees F in a protected dry location. Refer to the current Safety Data Sheet (SDS) for this product before handling, mixing, or applying. Use appropriate personal protective equipment and ensure adequate ventilation during application and cure. Dispose of material, containers, solvents, etc., per Federal, State and local guideline, rules and laws

TEST DATA

Test data has been gathered from testing conducted by independent, internal and third party testing. The best way to compare coating performance is by head-to-head independent testing as this removes the numerous variables found between testing standards, equipment and testing agencies.

TYPICAL VALUES

The information here is general information to help our customers determine whether our products suit their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products. Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is the replacement of our materials, and we shall not be liable for incidental or consequential damages. Polymer Nation Chemical Company LLC, 405 Oakwood Ave. Waukegan, IL 60085. All rights reserved.