

POLYUREA AND POLYASPARTICS

F-81 LV

TECHNICAL DATA SHEET

COMPONENTS

2

SOLIDS

83%

VOC

165 g/L

MIX RATIO

1:1

DESCRIPTION

F-81 combines our fast polyaspartic resin with our proprietary aliphatic hardener blend to create a fast speed, clear polyaspartic. F-81 is a 83% solids, low odor, low viscosity polyaspartic that provides the skilled installer with a short working time- fast dry time material that will allow for multiple steps to be completed in one day.

RECOMMENDED USES

F-81 is primarily used as a 1-day floor system. It can go direct to concrete as a primer and broadcast resin and be ready for recoat within 2 hours. It has excellent UV, abrasion and hot tire resistance.

LIMITATIONS

F-81 is designed to be applied between 6-15 mils as a topcoat for floors and 5-6 mils as a topcoat on walls. Ideal application temperatures to be between 40-80°F and 60% RH or less. Cooler temperatures will increase cure times. Warmer temperatures will decrease working and cure times.

SURFACE PREPARATION

The preparation method for each project is determined by a full understanding of the substrate to be coated, the chemistry of the coating system being used, the coating system thickness, and numerous other factors. The coating installer should fully read and understand ICRI Guideline NO.310.2R-2013 and OSHA 29 CFR 1926.1153 before starting preparatory work. The aim, of preparing a substrate for coating applications, is to roughen the surface, remove weak layers, contaminants, dirt, debris and present a solid, clean, dry substrate for the primer. If unsure as to the level of preparation needed contact Polymer Nation at techservice@polymernation.com

MIXING

It is always recommended to mix the entire kit, whenever possible, to avoid off-ratio mixtures. Mix ratio is 1 part F-81 Part A to 1 part F-81LV Part B. Combine all of part A and B into a single container, large enough to except the entire kit. Mix using a 350 RPM mixer using an appropriate mixing blade for 1 - 2 minutes making sure to not introduce excessive air into the material.

APPLICATION

...using a 3/8" nap roller cover...

COMPONENTS



Part A



Part B

GENERAL PRODUCT INFORMATION

Chemistry	Polyurea and Polyaspartics
Color / Finish	Clear and Color Packs
Number of Components	2
Solids by Volume	83%
VOC (Mixed)	165 g/L
Mix Ratio	1:1
Mixed Viscosity	230-250 cP
Gel / Working Time	7-12 minutes
Application Temperature	40-80°F
Odor	Very Subtle

It is always recommended to mix the entire kit, whenever possible, to avoid off-ratio mixtures

25°C/77°F. Warmer temperatures will reduce viscosity and lower temperatures will increase viscosity

60% RH or less

PHYSICAL PROPERTIES

Hardness	20 @ 24 hours / 50 @ 7 days	Pendulum Hardness (König)
Tensile Strength	3,270 psi	ASTM C307
Compressive Strength	12,500 psi	ASTM C579
Flexural Strength	5,550 psi	ASTM C580
Abrasion – Taber CS-17	0.022g Loss (when higher abrasion resistance is required the addition of PC 1336 to the coating should be included)	ASTM D4060
Impact Resistance	>160 inch pounds	ASTM D2794
Adhesion to Concrete	>450 psi Substrate failure	ASTM D7234
Gloss @ 60°	>90	
Accelerated Weathering	Non-yellowing	ASTM G154
Moisture Absorption	<.2 weight increase	ASTM C413
Coefficient of Thermal Lineal Expansion	15-17 x 10-6 27-30 x 10-6	ASTM C531
Water Vapor Transmission	See ASTM D3010	ASTM D1653
Independent Certificate – Third-Party Testing	N/A	ASTM D3010
Adhesion	5A	ASTM D3359
Adhesion to Steel	>1,000 psi	ASTM D4541
Hiding Power	2-5/175 When pigmented	ASTM D5150
Flammability When Adhered to Concrete	Self-Extinguishing	ASTM D635
Coefficient of Friction – Dry	0.75	NFSI B101.0
Coefficient of Friction – Wet	0.7	NFSI B101.1

CURE SCHEDULE

Dry to Touch	0.5-1 hours
Through Dry	1-2 hours
Dry to Walk	2.5-5 hours
Dry to Light Use	10-12 hours
Full Cure	7 days

COVERAGE & PACKAGING

Coverage Rate	110 – 300 sq. ft./gal.
Application Thickness	5-15 mils
Recoat Window	2-24 hours
Packaging	3, 15, 10 Gallon kits

STORAGE, HANDLING & SAFETY

Store at 60-80 degrees F. Store material between 60-80 degrees F in a protected dry location. Refer to the current Safety Data Sheet (SDS) for this product before handling, mixing, or applying. Use appropriate personal protective equipment and ensure adequate ventilation during application and cure. Dispose of material, containers, solvents, etc., per Federal, State and local guideline, rules and laws

TEST DATA

Test data has been gathered from testing conducted by independent, internal and third party testing. The best way to compare coating performance is by head-to-head independent testing as this removes the numerous variables found between testing standards, equipment and testing agencies.

TYPICAL VALUES

The information here is general information to help our customers determine whether our products suit their specific applications. Our products are intended for sale to commercial and industrial customers. We require that customers inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products. Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is the replacement of our materials, and we shall not be liable for incidental or consequential damages. Polymer Nation Chemical Company LLC, 405 Oakwood Ave. Waukegan, IL 60085. All rights reserved.